

MR Quality	MR-90	MR-33
Al ₂ O ₃ (%)	90.0	74.0
Fe ₂ O ₃ (%)	0.2	0.2
SiO ₂ (%)	6.0	13.0
ZrO ₂ (%)	-	12.0
B.D. gm/cc	2.95	3.00
A.P.(%)	18	18
C.C.S. kg/cm ²	700	800
P.C.E Orton	38	34
R.T.E.(%)	0.70	0.68
T.C.w/m°K	2.02	2.06
T.S.R	Good	V.Good

Application Recommendation

Orifice Rings	-	-
Spouts	-	×
Tubes	-	××
Plungers	×××	××
Stirrers	×××	××
Spout Burner / Cover	-	××
Forehearth	-	××
Mandral Sleeve & Trough etc.	-	##