

MR Quality	MR-35	MR-15
Al ₂ O ₃ (%)	49.0	68.0
Fe ₂ O ₃ (%)	0.2	0.2
SiO ₂ (%)	15.0	12.0
ZrO ₂ (%)	35.0	19.0
B.D. gm/cc	3.20	3.10
A.P.(%)	18	20
C.C.S. kg/cm ²	900	800
P.C.E Orton	36	34
R.T.E.(%)	0.62	0.60
T.C.w/m°K	2.20	2.04
T.S.R	V.Good	V.Good

Application Recommendation

Orifice Rings	xxx	***
Spouts	xxx	***
Tubes	xxx	***
Plungers	xxx	***
Stirrers	xxx	***
Spout Burner / Cover	-	-
Forehearth	-	-
Mandral Sleeve & Trough etc.	-	-