

MR Quality	MR-22S
Al ₂ O ₃ (%)	52
Fe ₂ O ₃ (%)	0.3
SiO ₂ (%)	17.0
ZrO ₂ (%)	29.0 (min)
B.D. gm/cc	3.00
A.P. (%)	18
C.C.S. kg/cm ²	900
P.C.E Orton	36
R.T.E. (%)	0.62
T.C.w/m ^o K	2.20
T.S.R	Exeellent

Application Recommendation

Orifice Rings	---
Spouts	---
Tubes	xxx
Plungers	xxx
Stirrers	xxx
Spout Burner / Cover	-
Forehearth	-
Mandral Sleeve & Trough etc.	-