

MR Quality	MR-22S	MR-33
Al ₂ O ₃ (%)	52	74.0
Fe ₂ O ₃ (%)	0.3	0.2
SiO ₂ (%)	17.0	13.0
ZrO ₂ (%)	29.0 (min)	12.0
B.D. gm/cc	3.00	3.00
A.P. (%)	18	18
C.C.S. kg/cm ²	900	800
P.C.E Orton	36	34
R.T.E. (%)	0.62	0.68
T.C.w/m ^o K	2.20	2.06
T.S.R	Exeellent	V.Good

Application Recommendation

Orifice Rings	---	-
Spouts	---	x
Tubes	xxx	xx
Plungers	xxx	xx
Stirrers	xxx	xx
Spout Burner / Cover	-	xx
Forehearth	-	xx
Mandral Sleeve & Trough etc.	-	##